

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



B8

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁵ : A61L 27/00, A61K 31/54</p>	<p>A1</p>	<p>(11) International Publication Number: WO 90/06138 (43) International Publication Date: 14 June 1990 (14.06.90)</p>
<p>(21) International Application Number: PCT/GB89/01423 (22) International Filing Date: 28 November 1989 (28.11.89) (30) Priority data: 8827986.4 30 November 1988 (30.11.88) GB (71) Applicant (for all designated States except CH US): HOLMES, Michael, John [GB/GB]; Frank B. Dehn & Co., Imperial House, 15-19 Kingsway, London WC2B 6UZ (GB). (71) Applicant (for all designated States except US): ED GEIST- LICH SÖHNE A.G. FÜR CHEMISCHE INDUSTRIE [CH/CH]; Wolhusen, CH-6110 Lucerne (CH). (72) Inventor; and (75) Inventor/Applicant (for US only) : PFIRRMANN, Rolf, Wil- helm [CH/CH]; Schadrudistrasse 27, CH-6006 Lucerne (CH).</p>		<p>(74) Common Representatives: HOLMES, Michael, John et al.; Frank B. Dehn & Co., Imperial House, 15-19 Kingsway, London WC2B 6UZ (GB). (81) Designated States: AT (European patent), BE (European patent), CH, DE, ES (European patent), FR (European patent), GB, IT (European patent), JP, LU (European patent), NL, SE (European patent), US. Published With international search report.</p>
<p>(54) Title: IMPLANT FOR USE IN BONE SURGERY</p> <p>(57) Abstract</p> <p>A lyophilised collagen sponge for use as an implant in osteitis and other bone cavities, said sponge having dispersed there- in antibacterially effective quantities of taurolidine and/or taurultam.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	ES	Spain	MG	Madagascar
AU	Australia	FI	Finland	ML	Mali
BB	Barbados	FR	France	MR	Mauritania
BE	Belgium	GA	Gabon	MW	Malawi
BF	Burkina Faso	GB	United Kingdom	NL	Netherlands
BG	Bulgaria	HU	Hungary	NO	Norway
BJ	Benin	IT	Italy	RO	Romania
BR	Brazil	JP	Japan	SD	Sudan
CA	Canada	KP	Democratic People's Republic of Korea	SE	Sweden
CF	Central African Republic	KR	Republic of Korea	SN	Senegal
CG	Congo	LI	Liechtenstein	SU	Soviet Union
CH	Switzerland	LK	Sri Lanka	TD	Chad
CM	Cameroon	LU	Luxembourg	TG	Togo
DE	Germany, Federal Republic of	MC	Monaco	US	United States of America
DK	Denmark				

IMPLANT FOR USE IN BONE SURGERY

5 This invention relates to a novel collagen- based sponge material for use as an implant in bone surgery.

 The treatment of osteomyelitis and osteitis is notoriously difficult. It is necessary to remove all infected bone material and then to induce remodel- ing,
10 that is re-growth of healthy bone tissue, within the cavity as formed. Unfortunately, re- infection is common and it is necessary that a powerful antibacterial substance is present during the remodelling phase. Remodelling in facio-maxillary surgery and tooth
15 extraction socket filling imposes similar requirements.

 In our European Patent No. 48558 we have described resorbable aqueous gels comprising cross- linked gelatin or collagen materials containing antibiotics such as gentamycin or more preferably, taurolidine, for
20 implantation into osteitis cavities. While such gels have proved successful for most purposes, there is a need for alternative implant materials, particularly for implantation into cavities in small bones such as those of the fingers and toes, as well as tooth
25 extraction cavities and other relatively small cavities.

 We have now found that a lyophilised sponge of collagen fibres containing the antibacterial substances taurolidine and/or taurultam provide an extremely effective implant material for such uses. Although
30 collagen sponges have been proposed which contain cross-linked or otherwise pre-treated collagen fibres together with an antibiotic such as gentamycin, it has not previously been proposed to impregnate such sponges with taurolidine and taurultam, which have particular
35 advantages in treating bone cavities and bone injuries generally.

 According to the present invention we provide a

lyophilised collagen sponge for use as an implant in osteitis and other bone cavities, said sponge having dispersed therein antibacterially effective quantities of taurolidine and/or taurultam.

5 Taurolidine and taurultam are methylol transfer agents which are able to combat not only gram negative and gram positive bacteria but also the exotoxins and endotoxins they produce. They are thus particularly well suited for the treatment of bone cavities liable to
10 re-infection. The soluble collagen sponge according to the invention releases the active substances firstly by diffusion and then by dissolution or resorption of the collagen. The sponge conveniently contains from 1-30 mg/cm² of taurolidine and/or from 1-60 mg/cm² taurultam.

15 Collagen fibres are the most common type of fibres in the connective tissue and the commonest protein in the human body, corresponding to 30% of the total protein. The hyaline cartilage material of the bone consists of 40-45% of collagen fibres. Human bone
20 contains about 40g collagen nitrogen per kg. Collagen fibres consist of collagen fibrils having diameters of 0.2 to 0.5 microns. Their peptide structure contains a high level of proline (12%) and hydroxyproline (10%) residues. Each fibril consists of overlapping molecules
25 of tropocollagen each of which includes a superhelix of 3 polypeptide alpha- chains, which are interwound and stabilised by hydrogen bonding and have terminal non-helical telopeptide sequences.

30 Four types of collagen are recognised, in which the tropocollagen is built up from three different polypeptide alpha-chains with an average molecular weight of 100,000. The commonest is Type I, occurring for example in skin, muscle, bone, tendons and fascia, which consists of two identical alpha-1-chains and one
35 alpha-2- chain with a different amino acid sequence. Types II, III, and IV consist of three alpha-1-chains which differ in their primary structure in different

parts of the body. Type II is the most common collagen type in the hyaline cartilage. Type III occurs inter alia, in the blood vessels and in foetal membranes. Type IV occurs in the basal laminae.

5 There are significant differences between collagen fibres at different conditions of maturity. Where the connective tissue is in an active phase of fibrillogenesis, for example during growth or wound healing, collagen fractions can be isolated with different
10 properties. The first fraction is extractable by neutral solutions (neutral-soluble collagen); this consists of recently synthesised tropocollagen molecules which are not aggregated or are only beginning to aggregate. The second fraction is extractable by a
15 sodium citrate solution at pH 3.0, and is thus termed the acid-soluble collagen fraction. The third fraction found in older tissues is the insoluble fraction and can only be extracted by very vigorous methods. One basis for the difference between these fractions lies in the
20 degree of cross-linking by oxidation to produce peroxide bridges. Collagen can also be cross-linked chemically via free amino groups, using aldehydes such as formaldehyde or glutaraldehyde or isocyanates such as hexamethylene diisocyanate. By such cross-linking,
25 animal collagen fractions lose their antigenicity almost completely. Cross-linking of collagen fibrils in this way is for example, made use of in heart replacement surgery, where animal, e.g. porcine, valves are conditioned with glutaraldehyde for use as human
30 pulmonary or mitral valve replacements.

 In general, it is preferred that the collagen is water insoluble but is rapidly resorbed eg within up to 12 hours, for example within 6 to 12 hours. This is compatible with the relatively short half-life of
35 taurolidine and taurultam. Aged or acid soluble collagen may thus be used or, more preferably, neutral soluble collagen fibres may be artificially aged by

oxidation, eg using a peroxide such as hydrogen peroxide, to form oxygen bridges. Collagen of type I, especially from skin and tendons, advantageously from the flank skin of young calves, is preferred.

5. However, it may be beneficial to lightly cross-limits neutral soluble collagen, eg by treatment with a cross-linking agent, for example an aldehyde such as formaldehyde or glutaraldehyde or a isocyanate such as hexamethylene diisocyanate. Such a cross-linked form
10 of collagen will be resorbed more slowly and thus may release the taurolidine or taurultam over a longer period. It is particularly preferred, however, that the level of any cross-linking is much that the collagen is resorbed in 12 hours or less after implantation.

15 Where the collagen is cross linked it may be beneficial to include an emulsifying agent, during the foaming and lyophilising step eg lecithin and/or Cremophor EL (available from BASF), both of which are parenterally acceptable.

20 Suitable collagen sponge may be obtained commercially, for example from Pentapharm AG of Basel, Switzerland, from Dr Otto Suwelak GmbH of Billerbeck, West Germany or from Ed Geistlich Söhne A.G. of Wolhusen, Switzerland. Alternatively, such material may
25 be obtained from the appropriate tissues by conventional methods.

Thus, for example, bovine skin, advantageously from young calves, and preferably from the flank region, may be chemically dehaired and mechanically split to
30 separate off the epidermis and the underskin with associated fat. It is important to avoid or minimise contamination with fat. The layer so obtained may be treated with mild alkali, such as calcium hydroxide, eg for about 4 weeks. The resulting material may then be
35 acidified, eg with 3% hydrochloric acid, washed with running water and comminuted. A proteolytic enzyme may be used to assist separation of collagen from other

proteins and a lipase may be used to remove residual fat. However, it is important to avoid antigenic reactions which may result from the use of such enzymes.

The neutral-soluble collagen so produced may then
5 be treated with an oxidising agent such as hydrogen peroxide to form oxygen bridges similar to those formed in the natural ageing of collagen.

The comminuted product may then be homogenised with about 7 parts by weight of water, the pH adjusted to
10 about 5.3 and the product further homogenised to produce a foam.

The foamed homogenised material is then filled into cooling cells, e.g. to a depth of about 1.5 cm, rapidly cooled to -20°C and lyophilised.

15 The incorporation of the taurolidine or taurultam may be effected either by foaming a collagen solution containing e.g. 2% taurolidine or taurultam, prior to lyophilisation or by redissolving lyophilised collagen in a solution of taurolidine or taurultam and
20 re-lyophilising.

The lyophilised collagen sponge material will normally be sealed in plastic containers and sterilised by radiation e.g. gamma radiation.

25 Sheets of the collagen sponge according to the invention may be conveniently about 0.5 cm in thickness. Such sheets can be readily cut by the surgeon into small shaped pieces for use as implants. They will normally be laid into the bone cavity without compression. If necessary, spongeosa may also be introduced into the
30 cavity at the same time.

The invention is illustrated by the following non-limiting Examples. Collagen GN is available from Ed. Geistlich Söhne A.G.

Example 1

Collagen GN (a fleecy material containing some collagen fibres, $21 \times 29.8 \text{ cm} = 625.8 \text{ cm}^2$) is soaked with 260g of a 4.8% (w/w) taurolidine solution and then immediately frozen. Freeze-drying gives a compact taurolidine-collagen sponge with 20 mg taurolidine/cm².

Example 2

Collagen GN ($21 \times 29.8 \text{ cm} = 625.8 \text{ cm}^2$) is soaked with 260g of a 4.8% (w/w) taurolidine solution, immediately frozen and then freeze-dried. The dried material is soaked a second time with 130g of a 4.8% (w/w) taurolidine solution and freeze-dried to give a compact taurolidine-collagen sponge with 30 mg taurolidine/cm².

Example 3

Collagen GN ($21 \times 29.8 \text{ cm} = 625.8 \text{ cm}^2$) is soaked with 250g of a 15% taurultam solution and immediately frozen. Freeze-drying gives a compact taurultam-collagen sponge with 60 mg taurultam/cm².

Example 4

Collagen GN ($21 \times 29.8 \text{ cm} = 625.8 \text{ cm}^2$) is soaked with 287.5g of a 13.05% taurultam solution and immediately frozen. Freeze-drying gives a soft taurultam-collagen sponge with 60 mg taurultam/cm².

Example 5

Collagen GN ($21 \times 29.8 \text{ cm} = 625.8 \text{ cm}^2$) is soaked with 537.5g of a 7% taurultam solution and immediately frozen. Freeze-drying gives a soft, downy taurultam-collagen sponge with 60 mg taurultam/cm².

Claims:

1. A lyophilised collagen sponge for use as an implant
in osteitis and other bone cavities, said sponge having
5 dispersed therein antibacterially effective quantities
of taurolidine and/or taurultam.
2. A collagen sponge as claimed in claim 1 wherein the
collagen is selected from acid soluble collagen and
10 artificially aged neutral soluble collagen, whereby the
resulting implant is capable of resorption in the human
body within up to 12 hours.
3. A collagen sponge as claimed in claim 1 or claim 2
15 wherein the collagen comprises type I collagen.
4. A process for the preparation of a collagen sponge
as defined in claim 1 in which a solution or suspension
of collagen fibres in an aqueous solution of taurolidine
20 or taurultam is lyophilised.
5. Use of a collagen sponge as defined in claim 1 in
surgery.

INTERNATIONAL SEARCH REPORT

International Application No **PCT/GB 89/01423**

I. CLASSIFICATION OF SUBJECT MATTER (if several classification symbols apply, indicate all) *

According to International Patent Classification (IPC) or to both National Classification and IPC

IPC5: A 61 L 27/00, A 61 K 31/54

II. FIELDS SEARCHED

Minimum Documentation Searched *

Classification System

Classification Symbols

IPC5

A 61 L; A 61 K

Documentation Searched other than Minimum Documentation
to the extent that such Documents are included in the Fields Searched *

III. DOCUMENTS CONSIDERED TO BE RELEVANT *

Category *	Citation of Document, ** with indication, where appropriate, of the relevant passages **	Relevant to Claim No. **
A	EP, A2, 0048558 (ED. GEISTLICH SÖHNE A.G. FÜR CHEMISCHE INDUSTRIE) 31 March 1982, see the whole document	1-5
A	US, A, 4789663 (D.G. WALLACE ET AL.) 6 December 1988, see the abstract, column 4, lines 1-17, lines 31-55, claims 1-5	1-3,5
A	WO, A1, 86/07265 (ED. GEISTLICH SOHNE A.G. FÜR CHEMISCHE INDUSTRIE) 18 December 1986, see the whole document	1-5

* Special categories of cited documents: **

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"Z" document member of the same patent family

IV. CERTIFICATION

Date of the Actual Completion of the International Search

26th February 1990

Date of Mailing of this International Search Report

19. 03. 90

International Searching Authority

EUROPEAN PATENT OFFICE

Signature of the International Searching Authority

T.K. WILLIS

III. DOCUMENTS CONSIDERED TO BE RELEVANT (CONTINUED FROM THE SECOND SHEET)		
Category *	Citation of Document, with indication, where appropriate, of the relevant passages	Relevant to Claim No.
A	EP, A2, 0139534 (ED. GEISTLICH SÖHNE A.G. FÜR CHEMISCHE INDUSTRIE) 2 May 1985, see the abstract, page 4, lines 30-34, claims -----	1

**ANNEX TO THE INTERNATIONAL SEARCH REPORT
ON INTERNATIONAL PATENT APPLICATION NO. PCT/GB 89/01423**

SA 32683

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report. The members are as contained in the European Patent Office EPP file on 08/11/89. The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A2- 0048558	31/03/82	JP-A- 57077616	15/05/82
		AU-D- 74861/81	11/03/82
		CA-A- 1190855	23/07/85
		US-A- 4587268	06/05/86
		AU-A- 554672	28/08/86
US-A- 4789663	06/12/88	EP-A- 0171176	12/02/86
		AU-D- 44643/85	09/01/86
		AU-A- 578108	13/10/88
		AU-D- 17511/88	27/10/88
		AU-D- 17515/88	27/10/88
WO-A1- 86/07265	18/12/86	EP-A- 0224545	10/06/87
		JP-T- 63500172	21/01/88
EP-A2- 0139534	02/05/85	BE-A- 900855	15/02/85
		AU-D- 34574/84	09/05/85
		JP-A- 60105617	11/06/85
		DE-A- 3438470	30/05/85
		US-A- 4604391	05/08/86
		CH-A- 660969	30/06/87